



DATASHEET


MODEL BB-125 VOLTAGE 6 MATERIAL Polypropylene DIMENSIONS Inches (mm) BATTER Deep-Cycle Flooded/Wet Lead-Acid Battery COLOR Maroon WATERING No Watering System available

BATTERY DIMENSIONS & TERMINAL CONFIGURATIONS









PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	VOLTAGE	CELL(S)	TERMINAL TYPE	DIM	ENSIONS INCHES (I	mm)	APPROX.WEIGHT LBS.(kg)
000	DD 405	C C	0		LENGTH	WIDTH	HEIGHT	(20)
GC2	BB - 125	0	3	DT-M8(A)	10.30 (262)	7.13 (181)	12.15 (289)	67 (30)

ELECTRICAL SPECIFICATIONS

CRANKING	PERFORMANCE	CAPACITY	(MINUTES)		CAPACITY	AMP-HOUR	S (A)	ENERGY (kWh)	INTERNAL RESISTANCE (mΩ)	SHORT CIRCUIT CURRENT (amps)
C.C.A@ 0° F (-18° C)	C.A.@ 32° F (0° C) @ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr		
	—	485	130	195	221	240	265	1.60	_	_

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77° F/25° C)							
SYSTEM VOLTAGE	6V	12V	24V	36V	48V		
Bulk Charge	7.41	14.82	29.64	44.46	59.28		
Float Charge	6.75	13.50	27.00	40.50	54.00		
Equalize Charge	8.10	16.20	32.40	48.60	64.80		

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.


CHARGING TEMPERATURE COMPENSATION


ADD	SUBTRACT
0.005V per cell for every 1°C bdow 25°C	0.005V per cell for every 1°C above 25°C
0.0028V per cell for every 1°F below 77°F	0.0028V per cell for every 1°F above 77°F

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE
-4° F to 113° F (-20° C to +45° C)At temperatures below 32° F (0° C) maintain a state of charge greater than 60%.	5 – 15% per month depending on storage temperature conditions











STATE OF CHARGE VS OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	SPECIFIC GRAVITY	CELL	6 VOLT
100	1.277	2.122	6.37
90	1.258	2.103	6.31
80	1.238	2.083	6.25
70	1.217	2.062	6.19
60	1.195	2.040	6.12
50	1.172	2.017	6.05
40	1.148	1.993	5.98
30	1.124	1.969	5.91
20	1.098	1.943	5.83
10	1.073	1.918	5.75





Self Discharge Characteristics

No supplementary charge required Α (Carry out supplementary charge before use if 100% capacity is required.) Supplementary charge required before use.Optional charging way as below: 1. Charged for above 3 days at limted current 0.25CA and constant volatge 2.25V/cell. В 2.Charged for above 20hours at limted current 0.25CA and constant volatge 2.45V/cell. 3.Charged for 8~10hours at limted current 0.05CA Supplementary charge may often fail to recover the capacity. С The battery should never be left standing till this is reached.

RECYCLE RESPONSIBLY



Thenumbeof minutes a battery can deliver when discharged at a constant rate at 80° F (27° C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance. Α.

- B. The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80° F (27° C) and maintain a voltage above 1.75 V/cell. Capacities are based on peak performance.
 C. Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.
 D. C.C.A. (Cold Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0° F (-18° C) at a voltage above 1.2 V/cell.

- C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32° F (0° C) at a voltage above 1.2 V/cell. This is sometimes referred to as MCA @ 32° F. Е.
- E. Height taken from bottom of the battery to the highest point on the battery. Heights may vary based on terminals
- G. Terminal images are representative only.

н. Weight may vary.

The tech data is just for reference and subject to change without prior notice.